

Tradeseal MS: Polymer Sealant

Code:RC13103

General Descriptions

Tradeseal MS is a high quality single component joint sealant with high adhesive strength. It is based on MS-Polymer, chemically neutral and fully elastic. Tradeseal MS is formulated for use in low movement joints in construction, automotive, marine and aerospace areas where a tough flexible rubber is required.

Physical Data

Base	Hybrid Polymer
Consistency	Stable Paste
Curing System	Moisture Cure
Skin Formation	10 min (20°C/65% relative humidity)
Curing Rate:	2-3mm/24h (20°C/65% R.H.)
Hardness:	45 ± 5 Shore A
Shrink	none
Specific Gravity	1.67 g/ml
Temperature resistance	-40°C until +120°C
Elongation at break	750% (DIN 53504)
Elasticity modulus 100%	0.75 N/mm ² (DIN 53504)
Tear Strength	1.8 N/mm ² (DIN 53504)
Elastical Recovery	>75%
max allowed distortion	20% ±

Packaging and Colours

Colours: White – Clear – Grey (Near Glass Clear) (other colours on request)

Packaging: Thick wall cartridge of 290 ML

Application

- All sealing and bonding applications in the building and metal industry
- Structural bonding in vibration constructions

Surface preparation:

Clean, dry and free from dust, grease and any other contaminants. Non porous surfaces may be primed with TGP Surface Activator.

Application method:

Manual or pneumatic caulking gun

Application temperature:

+1°C until +30°C

Cleaning:

Clean with white spirits immediately after application

Finishing:

Smoothen joint with a soapy solution before skin forming

General Information

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C

Chemical resistance

Good:

Water

Aliphatic Solvents

Mineral Oils

Grease

Diluted Inorganic acids and alkalis

Bad:

Aromatic Solvents

Concentrated Acids

Chlorinated hydrogen

Joint Size

Min. Width: 2mm in bonding applications
5mm in joints

Max. Width: 10mm in bonding applications
30mm in joints

Min. Depth: 5mm in joints

Recommendation: Width of joint = 2 times width of joints



Experts in
Rubber

Transport Information:

Road:	ADR	Free
Maritime:	IMDG	Free
Air:	ICAO/IATA-DGR	Free
UN:	None	Does not Apply

Labelling:

No danger labelling required.

Information

Tradeseal MS may be overpainted, however, due to the large number of paints and varnishes available we strongly recommend a compatibility test prior to application. The drying time of alkyd resin paints may increase.

E: sales@therubbercompany.com
W: www.therubbercompany.com

The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.